

Technical file quality 1537

29/05/2012

Quality : 100% polyester, brushed

Width : 148 cm +/- 3% methode: ISO 22198:2006

Weight : 106 gr/m2 +/- 3% methode: ISO 3801 - 1977

Shrinkage Warp / Weft 30°C : -0,5% / -0,5 %

Tear force methode: ELMENDORF ISO 13937 – 1:2000

- the warp yarns tear at : 1,5 [kg]

- the weft yarns tear at : 0,9 [kg]

Breaking load methode: ISO 13934-1:1999

- the warp yarns tear at : 85 [kg]

- the weft yarns tear at : 42 [kg]

Colorfastness to washing at 30°C: methode: ISO 105-C06:2010

	light shades	dark shades
- staining in PES	: 4/5-5	4-4/5

- staining in cotton	: 4/5-5	4-4/5
----------------------	---------	-------

- colorchange	: 4/5-5	4/5-5
---------------	---------	-------

Colorfastness to rubbing:

Rubbing dry	: 4/5-5	4-5
-------------	---------	-----

Rubbing wet	: 4/5-5	4-5
-------------	---------	-----

Care instruction:



Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.