

## Technical file quality 7001

01/07/2005

<b>Quality</b>	<b>: 100% PAD + 2x PU coating</b>	
<b>Width</b>	<b>: 154 cm +/- 3%</b>	<b>methode: ISO 3832 – 1976</b>
<b>Weight</b>	<b>: 75 gr/m2 +/- 3%</b>	<b>methode: ISO 3801 - 1976</b>
<b>Density</b>	<b>: 42 x 31</b>	
<b>Shrinkage Warp / Weft 30°C</b>	<b>: -2% / -2 %</b>	
<b>Tear force</b>		<b>methode: ELMENDORF ISO 13937 - 1</b>
- the warp yarns tear at	<b>: 1,1 [kg]</b>	
- the weft yarns tear at	<b>: 0,77 [kg]</b>	
<b>Breaking load</b>		<b>methode: ISO 5081</b>
- the warp yarns tear at	<b>: 76 [kg]</b>	
- the weft yarns tear at	<b>: 51 [kg]</b>	
<b>Colorfastness to washing at 30°C:</b>		<b>methode: ISO 105-C06:1994</b>
- staining in PAD	<b>: 4-5</b>	
- staining in cotton	<b>: 4-5</b>	
- colorchange	<b>: 4-5</b>	
<b>Rubbing dry</b>	<b>: 4-5</b>	
<b>Rubbing wet</b>	<b>: 4</b>	
<b>Water column /mm/</b>	<b>:1000</b>	<b>methode: ISO 811</b>
<b>Spray test</b>	<b>:100</b>	<b>methode: ISO 4920</b>

**Care instruction:**



**Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.**