

Belgian Textile Association

• B • T • A • SR, s.r.o.

Budovateľská 38, 080 01 Prešov

Technical file quality 7004

19/02/2008

Quality	: 100% polyester reflective + PQ coating /EN 471/		
Width	: 154 cm +/- 3%		methode: ISO 3832 – 1976
Weight	: 130 gr/m2 +/- 3%		methode: ISO 3801 - 1976
Density	: 25 x 23		
Shrinkage Warp / Weft 30°C	: 0% / 0%		
Tear force			methode: ELMENDORF ISO 13937 - 1
- the warp yarns tear at	: 0,8	[kg]	
- the weft yarns tear at	: 0,7	[kg]	
Breaking load			methode: ISO 5081
- the warp yarns tear at	: 84	[kg]	
- the weft yarns tear at	: 75	[kg]	
Colorfastness to washing at 30°C:			methode: ISO 105-C06:1994
- staining in PES	: 4-5		
- staining in cotton	: 4-5		
- colorchange	: 4-5		
Rubbing dry	: 4-5		
Rubbing wet	: 4-5		
Water column /mm/	: 2000		methode: ISO 811
Spray test	:100		methode: ISO 4920

Care instruction:



Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.

Tel.: 00421 (0) 51- 77 21 635, 6, 7 , Fax: 00421 (0) 51- 7724 293